

# Certificate of Test

QUOTE No.: NC6958

REPORT No.: FNC10849

"Copyright CSIRO 2013 ©"  
Copying or alteration of this report  
without written authorisation from CSIRO is forbidden.

## COMBUSTIBILITY TEST FOR MATERIALS

TRADE NAME: Zero Ladder

SPONSOR: Accommodation @ Australia Pty Ltd  
50 Prospect Street  
Wynnum  
BRISBANE QLD 4178  
AUSTRALIA

### DESCRIPTION OF TEST SAMPLE:

The sponsor described the tested specimen as aluminium gutter guard mesh. The specimen was constructed using several pieces of 40-mm diameter aluminium discs assembled to form 50-mm height.

Nominal thickness of disc: 1.30 mm  
Nominal total thickness: 50 mm  
Nominal density: 597 kg/m<sup>3</sup>  
Colour: silver

TEST PROCEDURE: Five (5) samples were tested in accordance with Australian Standard 1530 Methods for fire tests on building materials, components and structures, Part 1- 1994: Combustibility Test for Materials.

RESULTS: Mean furnace thermocouple temperature rise ..... 7.62°C  
Mean specimen centre thermocouple temperature rise..... 12.44°C  
Mean specimen surface thermocouple temperature rise ..... 12.54°C  
Mean duration of sustained flaming ..... 0 seconds  
Mean mass loss..... 0.32 %


DESIGNATION: The material is NOT deemed COMBUSTIBLE according to the test criteria specified in Clause 3.4 of AS 1530.1-1994.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

DATE OF TEST: 26 June 2013

Issued on the 22<sup>nd</sup> day of July 2013 without alterations or additions.

  
Heherson Alarde  
Testing Officer

  
Brett Roddy  
Team Leader, Fire Testing and Assessments



This document is issued in accordance with NATA's accreditation requirements.  
Accreditation No. 165 – Corporate Site No. 3625



**CSIRO Materials Science and Engineering**  
14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA  
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555